

# gloveon Paloma



## Nitrile Exam Gloves Powder Free, Standard Cuff

To don **Paloma** is like putting on a second skin. Its absolute tactility commends it to delicate procedures and jobs plus an assured tensile strength and resistance to chemical expected of a nitrile glove. You owe it to yourself to try this exceptional nitrile glove from **GloveOn**.



GloveOn Paloma		
<b>Length (mm)</b>	≥ 230	
<b>Thickness Measurements (mm)</b>		
Palm (centre of Palm)	0.07 ± 0.02	
Finger (13mm ± 3mm from tip)	0.09 ± 0.02	
<b>Physical Properties</b>	<b>Before Ageing</b>	<b>After Ageing</b>
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
<b>Inspection Levels &amp; AQL</b>	<b>Inspection Level</b>	<b>AQL</b>
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Physical Properties	S2	4.0
Visual Inspection (Major)	S4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove

### FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Violet blue colour

### PACKAGING

100 gloves per box  
10 boxes per carton

### REGULATORY COMPLIANCE

FDA 510(k), MDD 93/42/EEC,  
REACH, ROHS Directive 2002/95/EC,  
EC 10/2011, EC 1935/2004

### STANDARDS

ASTM D6319, ASTM D412, ASTM D573,  
ASTM D5151, ASTM D6124,  
EN455 part 1, 2, 3 & 4, EN 1186,  
EN 13130, CEN/TS 14234

### MANUFACTURING ACCREDITATIONS

ISO 9001  
ISO 13485  
EN ISO 13485

Chemotherapy Drugs and Concentration  
(Tested for Resistance to Permeation by Chemotherapy  
Drugs as per ASTM D6978-05)

Minimum Breakthrough  
Detection Time (minutes)

Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	Not recommended
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytosan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	Not recommended
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

**WARNING:** Gloves used for protection against chemotherapy drug exposure should be selected specifically for the type of chemicals being used. Due to the variety and concentration of chemotherapy drugs used in treatments, the resistance table shown does neither warrant nor imply the safe use of the gloves against chemotherapy drugs resistance in every case. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.